

SYNTHETIC BUTYL RUBBER BK-1675M

BK-1675M is a product of isobutylene and isoprene copolymerization in methyl chloride medium. This type of rubber is used for production of medical articles.

CAS Number: 9010-85-9

Design specification: TU 2294-108-05766801-2001

PROPERTY	VALUE	TEST METHOD
Mooney Viscosity, ML 1+8 (125°C)	40-50	para. 4.3 of TU
Viscosity spread in one lot, max.	6	
Unsaturation, % mol.	1.4 - 1.8	para. 4.4 of TU
Loss of mass at drying, %, max.	0.40	para. 4.5 of TU
Stabilizer mass content, %	0.05 - 0.20	para. 4.6 of TU
Aqueous extract pH	6.5 - 7.5	para. 4.13 of TU
Tensile strength, MPa, min.	19	para. 4.7 of TU
Ultimate elongation, %, min.	600	para. 4.8 of TU
Modulus at 400% elongation, MPa, min.	7	para. 4.9 of TU
Ash mass content, %, max.	0.35	para. 4.10 of TU
Iron mass content, %, max.	0.020	para. 4.11 of TU
Antiagglomerate mass content, %, max.	1.2	para. 4.12 of TU

Supply form: 30±1 kg bales.

Packaging: Polyethylene film, paper bags, wooden and metal pallet boxes.

Transportation: Product is transported by all means of transport.

Storage: Rubber in pallet boxes should be stacked maximum three tiers high. Storage in warehouses, away from direct sun-rays, atmospheric precipitation and contamination.

Information contained in this document is provided to the best of our knowledge and is considered true as per revision date. This specification does not release the customer from obligation to check the product as to its suitability for intended area of usage. We do not accept any liability for loss and damage that may occur from the use of this information.